



Marchio depositato.

EREDI DOTT. SETTIMIO CINICOLA
BENTONITE S.A.S. – di Cinicola Filippo & C.
INDUSTRIA MINERARIA - ESTRAZIONE E LAVORAZIONE BENTONITE
20131 MILANO – Via A. Stradivari, 4
TEL. 026552626 FAX 026572934
STABILIMENTO IN CASTELNUOVO DELLA DAUNIA (FG)
Miniere in S. Croce di Magliano e Castelnuovo della Daunia
Sito Web: WWW.CINICOLA.NET
e-mail: cinicolafax@gmail.com
tel. – fax 0881515047

Pos. Mecc. MI 035333

C.C.I.A.A. MI 1149158

Trib. Soc. MI 230423

Cod. Fiscale e Part. IVA:
0707058 015 9

Codice Identificativo
Comunitario:
IT 0707058 015 9

SCHEDA TECNICA 2022

BENTONITE 7C TIPO ARB

Analisi chimica

SiO ₂ (%)	52,6
Al ₂ O ₃ (%)	12,7
CaO (%)	10,5
MgO (%)	2,2
Na ₂ O (%)	3,6
K ₂ O (%)	1,3
Fe ₂ O ₃ (%)	3,4
TiO ₂ (%)	0,4
SO ₃ (%)	0,2
MnO (%)	0,1
PF (%)	12,9

pH (sospensione 6%)

- 9-10

PROVE FISICHE (sospensione 6%)

- | | | |
|------------------------|---|--------------|
| • VISCOSITA' MARSH | = | 27 - 30 sec. |
| • LIMITE DI LIQUIDITA' | = | 150 - 250 |
| • DECANTAZIONE A 24h | = | 2 % - 4 % |
| • VISCOSIMETRIA FANN | = | 10 - 14 |

All the above information is believed to be accurate but is not warranted.
It doesn't represent any assurance of properties and fitness for use of the product.
Above mentioned specification may be changed without prior notice.